


LAKE PRODUCTS LTD

MANUFACTURERS AND DISTRIBUTORS

9 July 2014

Test Report for Silicone Rubber Component

A silicone rubber component – Lake Products' Pipetite tested to ASTM G 154-06.

<p>Sample</p> <p>Silicone Rubber Component – Pipetite</p> <p>Photo attached of test sample after 6,328 hours</p>	
<p>Test Details</p>	<p>ASTM G 154-06</p>
<p>QUV Equipment</p>	<p>Q-Lab</p>
<p>Model Number</p>	<p>QUV/SPRAY</p>
<p>Lamp Supplier</p>	<p>Q-Lab</p>
<p>Lamp Details</p>	<p>UVA-340</p>
<p>Test Duration Time</p>	<p>6,328 hours</p>
<p>Test Result:</p> <p>Using the "Standard Practice for Operating Fluorescent Light Apparatus for UV Exposure of Non-Metallic Materials" the sample photographed above completed 6,328 hours* as set out in ASTM G 154-06.</p> <p>*note: The typical test procedure used for G 154-06, outdoor exposure is 28 days or 672 hours</p> <p>Observation:</p> <p>No detrimental effect to the physical or mechanical properties of the sample.</p>	

Yours faithfully



Lake Products Ltd