

Technical Data Sheet

PU-UF3

A opaque transparent high gloss finish on both sides Poly Ether Urethane Thermo plastic film. Having no memory **PU-UF3** will not fracture as a result of constant flexing.

Advantages

- Superior flexibility
- o Excellent abrasion resistance
- Clear Transparent high clarity
- Smooth welded seams
- o Superior chemical resistance for CIP washing
- o Great aging resistance
- Non porous
- Smooth surface
- No material degradation



Applications

Stationary, Vibratory, Gyratory, Sifters, Screeners, Feeders, Spray driers, Fluid Bed, Static Cool Bed, Bin dischargers, Hoppers, Conveyors, Packing equipment, Storage silos, Screw conveyors, Valves, butterfly valves, Rotary valves, Tanks, Silo's, any sort of product handling equipment Air ducting, Fans, Inflatable seals, Covers, Outside protection sleeves, Bellows, Load cell (high volume, weight and capacity), Harmonica's, Telescopic applications, Vacuum formed shapes.

General Properties

Name: PU-UF3

Description :Poly Ether UrethaneColor :Opaque TransparentSurface :Gloss / Gloss (both sides)

Surface Roughness: -

Wall Thickness: 1,00mm / 0.0393 Inch (+/-10%)

Hardness: 87° Shore A
Tensile Strength: 60 MPa
Maximum Elongation: 550%

Operating Temperature : -40 °C to 90°C

-40 °F to +194 °F

Max. Surge Temp: $+120 \, ^{\circ}\text{C} \, / \, +248 \, ^{\circ}\text{F}$

Low Temperature Flexibility: Good **Air Permeability:** 0

Type of Material: Sheet on roll, 1500x50000mm

Pressure Resistance for Flexible Connectors

0,34 Bar / 5.0 PSI For temperatures up to 90 °C / 195°F

Please see "Operating Pressure Guide" for further information.

we recommend using the shortest possible connector for applications where increased pressure and/or high temperature is expected. Please contact us for more information.

Filcoflex B.V. Website: www.filcoflex.com

The Netherlands E-mail : info@filcoflex.com
Luxemburgstraat 3 Telephone : +31 (0) 416 764 764

5171 PK Fax: +31 (0) 416 764 763

Kaatsheuvel



Technical Data Sheet

Weighing Applications

High volume weight and capacity weighing and dosing applications please see "weighing and dosing guide" for further information.

Chemical Resistance

- o CIP resistant (see CIP chemicals guide)
- o Cleaning Chemicals (see cleaning guide)
- o For a detailed chemical resistance please see our chemical compatibility chart

ATEX & Explosion Safety

PU-UF3 has been tested for its electrostatic properties, and has been found ATEX compliant and safe to use in all dust explosion hazardous areas, such as ATEX zones 20, 21, 22.*



No propagating brush discharges could be determined. Non Conductive but safe to use up to a length of 1000mm.*

PU-UF3 has also been explosion pressure tested and found safe to up to an explosion pressure of 1,5 Bar.

Food Contact Compliancy

PU-UF3 complies with the following regulations for plastics in repetitive contact with foods:*

- United States
 - o FDA 21 CFR 177.1680
- European Community
 - o (EC) 1935/2004
 - o (EC) 10/2011
 - o (EC) 2023-2006
 - o (EC) 1907/2006 (REACH)



Website: www.filcoflex.com
E-mail: info@filcoflex.com

Fax: +31 (0) 416 764 763

Telephone: +31 (0) 416 764 764

We will be happy to advise further if you have any questions.

Filcoflex B.V.
The Netherlands
Luxemburgstraat 3
5171 PK
Kaatsheuvel

^{*} Some restrictions may apply, a copy of all certifications can be downloaded, or will be sent to you upon request.



Technical Data Sheet

Production Methods used

Joining / Bonding:

- o Welding
 - HF high frequency welding Welding the material and cooling it down under compression with Radio Frequency to make the TPU material flow nearly seamless to form a uniform thickness with the original material wall thickness.
 - Heat contact with silver alloy heating element Welds are welded surface to surface after which the weld are compressed while cooling.
 - Hot air hot filtered and conditioned contaminent-, oil- and greas- free compressed air

Cutting:

- Stainless Steel knives
- Water Jet cutting

Filcoflex B.V. The Netherlands Luxemburgstraat 3 5171 PK Kaatsheuvel

Website: www.filcoflex.com E-mail: info@filcoflex.com Telephone: +31 (0) 416 764 764

Fax: +31 (0) 416 764 763